



THOR Tarp

DIV. OF **ODIN** INTERNATIONAL, INC



DURASHIELD 9000 - SPECIFICATION SHEET

PROPERTIES

General:

Appearance	Black/White
% Light Transmission	0%
Coating	Laminated both sides
Thickness	± 12 mils average
Weight Per MSF	50 pounds

MECHANICAL

*1" strip tensile FTMS-191-5102	34.4 pounds
*Grab tensile FTMS-191-5100	83.7 pounds
*Tongue tear FTMS-191-5136	27.45 pounds
*Trapezoid tear FTMS-191-5136	46.15 pounds
Hydrostatic bursting point, PSI FTMS-191-5512	90

PERMEABILITY

Maximum use temperature °F	190°
Minimum use temperature °F	-70°

*Average of warp and fill

CORPORATE HQ: P.O. BOX 811 • OCONOMOWOC, WI 53066-0811 • 262-569-7171 • FAX: 262-569-1511
TOLL FREE: 1-888-ODIN-INC • 1-888-634-6462 • EMAIL: INFO@THORTARP.COM

WWW.THORTARP.COM