



ODIN International, Inc.

P.O. Box 811 • OCONOMOWOC, WI 53066-0811

TOLL FREE: 1-888-ODIN-INC
 PHONE: 1-262-569-7171
 FAX 1: 1-262-569-7170
 FAX 2: 1-262-569-1511
 EMAIL: INFO@ODININC.COM
 WWW.ODININC.COM

ThoroWeave 900 – Trampoline Fabric

Wicker-weave polypropylene

Mechanical Properties	Test Method	Unit	Typical Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D 4632	lbs	495	435
Trapezoid Tear Strength	ASTM D 4533	lbs	188	185
Mullen Burst Strength	ASTM D 3786	psi	825	
Abrasion	ASTM D4886	% strength retained	95	
Puncture Strength	ASTM D 4833	lbs	190	
UV Resistance (at 5000 hours)	ASTM G154 (QUV)	% strength retained	77	

Physical Properties	Test Method	Unit	Typical Value
Weight	ASTM D 5261	oz/yd ²	8.1
Thickness	ASTM D 5199	mils	19
Fiber Content			100% PP



THOR Tarps



THOR Namebuilder



ASGARD Web Services