



**THOR Tarp**  
DIV. OF **ODIN** INTERNATIONAL, INC



# ThoroWeave 400 Black Ground Cover Fabric

<u>TYPICAL PROPERTIES</u>	<u>TEST METHOD</u>	<u>AVERAGE VALUE</u>
Construction	ASTM D-3775	22 x 10.5
Tensile Strength	ASTM D-4632	175 lbs x 115 lbs
Elongation at Break	ASTM D-4632	24% x 20%
Burst Strength (Mullens)	ASTM D-3786	315 P.S.I.
Trap Tear	ASTM D-4533	75 lbs x 60 lbs
A.O.S. Standard Sieve	ASTM D-4571	40
Mass per Unit Area	ASTM D-5261	3.25 oz/yd <sup>2</sup>
Flow Rate (Falling Head)	ASTM D-4491	6 gpm/ft <sup>2</sup>
U.V. Resistance Strength Retained After 2500 Hours Carbon Arc Weatherometer	Fed. Std. #191 Method 5804	70%
Marker Yarns		12" Spacing

Seller makes no warranty, express or implied, concerning the products furnished hereunto other than that it shall be of the quality and specifications stated herein. ANY IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED AND TO THE EXTENT THAT IS CONTRARY TO THE FOREGOING SENTENCE, ANY IMPLIED WARRANTY OR MERCHANTABILITY IS EXPRESSLY EXCLUDED. Any recommendations made by Seller concerning uses or applications of said product are believed reliable and Seller makes no warranty of results to be obtained. This data sheet supercedes all previous data sheets for this style and is subject to change without notice.

CORPORATE HQ: P.O. Box 811 • OCONOMOWOC, WI 53066-0811 • 262-569-7171 • FAX: 262-569-1511  
TOLL FREE: 1-888-ODIN-INC • 1-888-634-6462 • EMAIL: INFO@THORTARP.COM

WWW.THORTARP.COM