



ODIN International, Inc.

P.O. Box 811 • OCONOMOWOC, WI 53066-0811

TOLL FREE: 1-888-ODIN-INC
 PHONE: 1-262-569-7171
 FAX 1: 1-262-569-7170
 FAX 2: 1-262-569-1511
 EMAIL: INFO@ODININC.COM
 WWW.ODININC.COM

ThoroWeave 950 – Woven Mesh Fabric *Monofilament Polypropylene*

Mechanical Properties	Test Method	Unit	Typical Roll Value	
			MD	CD
Grab Tensile Strength	ASTM D 4632	lbs	525	310
Trapezoid Tear Strength	ASTM D 4533	lbs	170	80
Mullen Burst Strength	ASTM D 3786	lbs	625	
Puncture Strength	ASTM D 4833	lbs	150	
Water Flow	ASTM D 4491	gpm	15	
Air Flow	ASTM D 737	cfm	>60	
Shade		%	95	
UV Resistance @ 500 hours	ASTM D 4355	%	90	

Physical Properties	Test Method	Unit	Typical Value
Weight	ASTM D 5261	oz/sq yd	6.2
Thickness	ASTM D 5199	mils	15
Fiber Content			100% PP



THOR Tarps



THOR Namebuilder



ASGARD Web Services